

EOS Aluminium Al2139 AM Material Data Sheet

EOS Aluminium Al2139 AM

Highest Strength Aluminum Alloy in AM

EOS Aluminium Al2139 AM is a 2000-series high strength alloy specifically designed for AM. It demonstrates outstanding performance in elevated temperatures up to 200 °C. Excellent strength properties include yield and tensile strength around 500 MPa in heat treated state and allow lightweight part design. The fast and simple heat treatment procedure enables an affordable part production.

Main Characteristics:

- Unmatched strength in temperatures between 50-200 °C
- Robust one-step heat treatment
- Parts can be electropolished and anodized

Typical Applications:

- Aerospace
- Racing
- Transportation & Mobility
- Lightweight designs


The EOS Quality Triangle

EOS uses an approach that is unique in the AM industry, taking each of the three central technical elements of the production process into account: the system, the material and the process. The data resulting from each combination is assigned a Technology Readiness Level (TRL) which makes the expected performance and production capability of the solution transparent.

EOS incorporates these TRLs into the following two categories:

- Premium products (TRL 7-9): offer highly validated data, proven capability and reproducible part properties.
- Core products (TRL 3 and 5): enable early customer access to newest technology still under development and are therefore less mature with less data.

All of the data stated in this material data sheet is produced according to EOS Quality Management System and international standards.



Powder Properties


The chemical composition of the EOS Aluminium Al2139 AM powder is modified from Aluminium Association Teal Sheet for Al2139 (wrought aluminum alloys).

Powder chemical composition (wt.-%)


Element	Approximate Composition
Al	Balance
Cu	4.5 - 5.5
Mg	>0.8
Ag	0.15 - 0.6
Mn	0.2 - 0.6
Zn	<0.25
Si	<0.1
Fe	<0.15
Cr	<0.05
V	<0.05
Other metallic additions	<4

Powder particle size

Generic particle size distribution	20-63 μm
------------------------------------	---------------------



SEM micrograph of EOS Aluminium Al2139 AM powder.



EOS Aluminium Al2139 AM for EOS M 290 | 60 μm

Process Information
Heat Treatment
Physical Part Properties
Mechanical Properties
Additional Data

EOS Aluminium Al2139 AM for EOS M 290 | 60 µm


Process Information

Process with good buildability, productivity and excellent mechanical properties after heat treatment also at elevated temperatures. Part and support design for high strength aluminium is required.

System set-up	EOS M 290
EOSPAR name	Al2139AM_060_CoreM291_110
Software requirements	EOSPRINT 2.7 or newer EOSYSTEM 2.11 or newer
Powder part no.	9030-0008
Recoater blade	HSS
Nozzle	EOS grid nozzle
Build platform temperature	175 °C
Inert gas	Argon
Sieve	75 µm

Additional information

Layer thickness	60 µm
Volume rate	7.2 mm ³ /s
Minimum wall thickness	0.4 mm



Chemical and Physical Properties of Parts¹

The chemical properties of the parts are the same as that of the powder.



Micrograph etched as manufactured

Defects	Result
Porosity	0.2 - 0.3 %
Density, ISO3369	≥ 2.84 g/cm ³


Typical mechanical properties

	Yield strength R _{p0.2} [MPa]	Tensile strength R _m [MPa]	Elongation at break A [%]
Heat treated vertical	460	520	4
Heat treated horizontal	460	540	6
As manufactured vertical	350	380	6
As manufactured horizontal	350	380	8

Tensile testing as per ISO 6892-1, B10

Typical hardness EN ISO 6506-1

Heat treated (T4)	162 HBW 2.5/62.5
As manufactured	112 HBW 2.5/62.5



Heat Treatment

EOS Aluminium Al2139 AM recommended

T4 Heat Treatment:

Solution annealing 45 min @ 490 °C, water quench.

Natural aging 3 days in room temperature.

Step 1:

Solution annealing of 45 minutes in 490 °C followed by immediate quenching to water.


Step 2:


Natural aging in room temperature for 3 days.

Additional Data¹

Elevated temperature properties

Elevated temperature tensile testing of EOS Aluminium Al2139 AM (T4) and a wrought grade reference material (T6 HT state) according to EN 2002-002.





EOS Aluminium Al2139 AM for EOS M 400-4 | 50 μm

Process Information

Heat Treatment

Physical Part Properties

Mechanical Properties

Additional Data

EOS Aluminium Al2139 AM for EOS M 400-4 | 50 µm

Process Information


High performance process with good microstructure and excellent mechanical properties and low anisotropy after heat treatment. Good mechanical properties at elevated temperatures in heat treated condition. Process offers good buildability of small features with soft recoating. Part and support design for high strength aluminium is required.

System set-up	EOS M 400-4
EOSPAR name	Al2139AM_050_CoreM404 1.00
Software requirements	EOSPRINT 2.10 or newer EOSYSTEM 2.14 or newer
Powder part no.	9030-0008
Recoater blade	HSS or soft
Nozzle	Standard
Build platform temperature	195 °C
Inert gas	Argon
Sieve	75 µm


Additional information

Layer thickness	50 µm
Volume rate	4x 5.0 mm ³ /s
Minimum wall thickness	0.4 mm

Chemical and Physical Properties of Parts¹



The chemical properties of the parts are the same as that of the powder.



Micrograph etched as manufactured

Defects	Result
Average defect percentage	0.1 %
Density, ISO3369	≥ 2.84 g/cm ³


Typical mechanical properties

	Yield strength R _{p0.2} [MPa]	Tensile strength R _m [MPa]	Elongation at break A [%]
Heat treated vertical	450	530	6
Heat treated horizontal	460	550	7
As manufactured vertical	380	430	8
As manufactured horizontal	380	430	10

Tensile testing as per ISO 6892-1, B10

Typical hardness EN ISO 6506-1

Heat treated (T4)	168 HBW 2.5/62.5
As manufactured	115 HBW 2.5/62.5



Heat Treatment

EOS Aluminium Al2139 AM recommended

T4 Heat Treatment:

Solution annealing 45 min @ 490 °C, water quench.

Natural aging 3 days in room temperature.

Step 1:

Solution annealing of 45 minutes in 490 °C followed by immediate quenching to water.


Step 2:

Natural aging in room temperature for 3 days.

Additional Data¹

Elevated temperature properties

Elevated temperature tensile testing of EOS Aluminium Al2139 AM (T4) and a wrought grade reference material (T6 HT state) according to EN 2002-002.



Headquarters

EOS GmbH
Electro Optical Systems
Robert-Stirling-Ring 1
D-82152 Krailling/Munich
Germany
Phone +49 89 893 36-0
info@eos.info

www.eos.info

 EOS

 EOSGmbH

 EOS.global

 EOSGmbH

#ShapingFuture

#ResponsibleManufacturing

Further Offices

EOS France
Phone +33 437 497 676

EOS Greater China
Phone +86 21 602 307 00

EOS India
Phone +91 443 964 8000

EOS Italy
Phone +39 023 340 1659

EOS Japan
Phone +81 45 670 0250

EOS Korea
Phone +82 2 6330 5800

EOS Nordic & Baltic
Phone +46 31 760 4640

EOS North America
Phone +1 877 388 7916

EOS Singapore
Phone +65 6430 0463

EOS UK
Phone +44 1926 675 110

Status 01/2023

EOS is certified according to ISO 9001. EOS® and EOSPRINT® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.

Cover: This image shows a possible application.

¹ Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein.

This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user.

